

RESIN GLASS



GLASS-FIBRE PUTTY

DEFINITION

Polyester putty reinforced with fibreglass to increase its resistance. Appropriate to repair such composites as polyester parts and rusted metallic areas. Creamy putty with very easy application properties. Very good adhesion on different surfaces.

PHYSICAL CHARACTERISTICS

Nature: Unsaturated polyester

Colour: Green

Specific weight: 1,6 kg/l at 20°C

VOC: 23 g/l Mixing Application

AUXILIARY PRODUCTS

Hardener PBO

SUITABLE SURFACES

It may be applied on steel or polyester.

When maximum protection is required apply on epoxy primer.


Do not apply on thermoplastic finishes and Wash Primers.

SURFACE PREPARATION


- 1 Identify surface.
- 2 Process:

| PROCESS | _ | 7 | Steel | Polyester UP-GFK |
|---------|------|---|-------|---------------------|
| | P80 | | ٧ | 1 |
| | P150 | | 4 | 7 |
| | DA93 | | 1 | 1 |

VERSIÓN: 151026 Pag: 2/2



| TIME | | | | |
|----------|--|--|--|--|
| 5 min | | | | |
| DISTANCE | | | | |
| 80 cm | | | | |
| TMAX. | | | | |
| 80°C | | | | |



REMARKS

It must be isolated with a polyester putty before applying primer. Do not add more hardener than specified. Mix thoroughly. Polyester putties will not harden at temperatures under +5°C.

EQUIPMENT CLEANING

Clean putty knifes with a cleaning thinner before the product hardens.

SAFETY

Follow instructions of product label. For more information check the Safety Data Sheets. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

GUARANTEE

In unopened original packaging, one year from manufacturing date.

For any technical information contact with our Customer Attention Service or our Technical Department. ROBERLO SA declines any responsibility due to an incorrect use of the product.