

VOTTELER LACKFABRIK  
GmbH & Co. KG  
Schwieberdinger Strasse 97/102  
70825 Korntal-Muenchingen  
Germany  
Phone:  
+49 711 98 04-5  
Fax  
+49 711 98 04-642  
eMail:  
d.info@votteler.com

VOTTELER AG  
LACKFABRIK  
Wiler Strasse. 3  
9536 Schwarzenbach SG  
Switzerland  
Phone:  
+41 71 929 52 82  
Fax  
+41 71 929 52 84  
eMail:  
ch.info@votteler.com

VOTTELER  
LACKTECHNIK GMBH  
Malvenstrasse. 7  
4600 Wels  
Austria  
Phone:  
+ 43 72 42 7 59-0  
Fax  
+ 43 72 42 7 59-113  
eMail:  
at.info@votteler.com



## PRODUCT DESCRIPTION

# 32055-0-0000

## PURIDUR® SANDING PRIMER, RAPIDO COLOURLESS

### Attributes / Characteristics

Rich in solid body PURIDUR® - fine sanding primer with good filling properties and rapid sandability is especially suitable for closed pored wood coatings and is applicable without insulating base in MDF coatings.

Marine Equipment guideline 96/98/EG.

This material has been tested for low-flame spread in accordance with Resolution MSC 61(67), FTP-Code, Annex 1, Part 5. EU Specimen approval procedure (Module B), Approval No.116.290, U.S. Coast Guard Approval No.164.112/EC0736/116.290. Low-flame spread certificate applies only when applied in combination with PURIDUR® Hardener 38055-0-0000 in the specified mixing ratio.

### Area of application

Wood and wooden composites

### Technical data

Gloss level	0*
Colour	Colourless - Votteler - 0000
Mixing ratio	100 parts lacquer 32055-0-0000 50 parts hardener 38055-0-0000
Thinner	19947-0-0000 SPECIAL THINNER
Retarder	39999-0-0000 RETARDER FOR PURIDUR®-LACQUERS
Density	0.955 – 0.975 g/ml at 20 °C
Pot life	approx. 2 hours at 20 – 23 °C
Shelf life when stored	
Unopened	12 months at 20 °C
Recommended	
Storage temperature	-10 – 30 °C

\*= Gloss level is defined by standardised methods. Gloss level depends on the quantity applied, method and drying conditions and the type of the substrate.

### Application

Application method	Spray application	Airless, Air mix, Cup Gun, Air Atomizing, 2C Plant Viscosity: 15 – 17 sec DIN 4 mm at 20 - 23 °C Nozzle size: 1.5 -1.8 mm Material pressure: 80 – 120 bar Atomizing pressure: 1.0 – 3.0 bar Air atomizing: 2.0 – 3.5 bar
Number of coats	2-3	
Coverage	110-180 g/m²	
Room temperature	20 – 25 °C	

The suitability of the material shall be inspected by the manufacturer with respect to his/her requirements regarding quality, color, and the like, e.g. by a sample staining and/or sample varnishing. The above information is based on our testing and experience. Furthermore, the information does not represent any warranty of any characteristics and thus does also not represent the contractually agreed nature of the product. Additionally, the information does not claim any completeness and it is given without any warranties.

VOTTELER LACKFABRIK  
GmbH & Co. KG  
Schwieberdinger Strasse 97/102  
70825 Korntal-Muenchingen  
Germany  
Phone:  
+49 711 98 04-5  
Fax  
+49 711 98 04-642  
eMail:  
d.info@votteler.com

VOTTELER AG  
LACKFABRIK  
Wiler Strasse. 3  
9536 Schwarzenbach SG  
Switzerland  
Phone:  
+41 71 929 52 82  
Fax  
+41 71 929 52 84  
eMail:  
ch.info@votteler.com

VOTTELER  
LACKTECHNIK GMBH  
Malvenstrasse. 7  
4600 Wels  
Austria  
Phone:  
+ 43 72 42 7 59-0  
Fax  
+ 43 72 42 7 59-113  
eMail:  
at.info@votteler.com



## PRODUCT DESCRIPTION

# 32055-0-0000

## PURIDUR® SANDING PRIMER, RAPIDO COLOURLESS

### Application

Optimal humidity	45 – 65%
Temperature of lacquer	20 – 25°C
Cleaning thinner	19995-0-0000
Pre-treatment of base and substrate	Apply on freshly sanded wood and wooden materials. A graded sanding is recommended. Brush wood pores clean before staining or priming.
Applicable on bleached Bases	No
Sanding	Substrate Grain 120 - 180 Lacquer Grain 280 – 400 Over coatable max. 4 hours after sanding .
Humidity of wood	7-10 %
Drying/Curing	Air drying Bone dry for approx. 15 – 20 min at 20 – 23°C / 40 – 65% relative humidity Sanding possible after approx. 2 – 3 hours at 20 – 23°C / 40 – 65% relative humidity Over coatable up to 1 hour at 20 – 23°C / 40 – 65% relative humidity
General instructions	Stir well before use and shake if necessary. Carry out a trial before use. Test adhesion. Local general guide lines for the processing of PUR materials are to be observed. Before application add the required components slowly and mix homogeneously. When using a retarder, note the extended drying period up to sanding and/or stacking. Observe the time intervals up to re-coating. For the marine sector, the wet application quantity should not exceed max. 260g/m <sup>2</sup> . The flame retardant surface active ingredient should not be applied on pipes, ducting or cables. For applications in the marine sector, the conformity declaration can be downloaded from <a href="http://www.votteler.com">www.votteler.com</a> . Not suitable for light coloured wood and light coloured bases. For yellowing resistant surfaces we recommend PURIDUR® fine sanding base 32087-0-0000. Once opened, ensure that the container is re-closed firmly. After repeated openings, check the suitability of material for the intended purpose.

The suitability of the material shall be inspected by the manufacturer with respect to his/her requirements regarding quality, color, and the like, e.g. by a sample staining and/or sample varnishing. The above information is based on our testing and experience. Furthermore, the information does not represent any warranty of any characteristics and thus does also not represent the contractually agreed nature of the product. Additionally, the information does not claim any completeness and it is given without any warranties.

VOTTELER LACKFABRIK  
GmbH & Co. KG  
Schwieberdinger Strasse 97/102  
70825 Korntal-Muenchingen  
Germany  
Phone:  
+49 711 98 04-5  
Fax  
+49 711 98 04-642  
eMail:  
d.info@votteler.com

VOTTELER AG  
LACKFABRIK  
Wiler Strasse. 3  
9536 Schwarzenbach SG  
Switzerland  
Phone:  
+41 71 929 52 82  
Fax  
+41 71 929 52 84  
eMail:  
ch.info@votteler.com

VOTTELER  
LACKTECHNIK GMBH  
Malvenstrasse. 7  
4600 Wels  
Austria  
Phone:  
+ 43 72 42 7 59-0  
Fax  
+ 43 72 42 7 59-113  
eMail:  
at.info@votteler.com



## PRODUCT DESCRIPTION

### 32055-0-0000

### PURIDUR® SANDING PRIMER, RAPIDO COLOURLESS

#### Disposal

In case of disposal, use only waste codes specified by your local authority.

#### Unit of sales

25.000 Kg in 30 litre container

5.000 kg in 6 Ltr. container

2.000 kg in 3 Liter container

#### Safety

Observe instructions on the safe data sheet (MSDS) and on the container label.

#### Test norms and durability

IMO Resolution MSC.61 (67), FTP-Code, Annex 1, Part 5 tested for fire behaviour as proof of low-flame spread.

#### Other instructions

For commercial and industrial use only.

#### Date of last update

10.05.2016

The suitability of the material shall be inspected by the manufacturer with respect to his/her requirements regarding quality, color, and the like, e.g. by a sample staining and/or sample varnishing. The above information is based on our testing and experience. Furthermore, the information does not represent any warranty of any characteristics and thus does also not represent the contractually agreed nature of the product. Additionally, the information does not claim any completeness and it is given without any warranties.