



S61 ONELIGHT BODY FILLER YELLOW

Universal ultra-light specific weight putty

A) DESCRIPTION AND FIELDS OF APPLICATION:

Universal putty with an ultra-light specific weight to treat every kind of surface, it characterizes for a very easy application by knife and an excellent compactness. Its specific formulation allows a particularly easy sanding, a very low permeability to humidity, a strong adhesion and an excellent finishing.

It is particularly suitable for nautical applications, industrial vehicles, buses, etc. every time the lightness is an important topic.

The sanding of a higher quantity composed by big particles allows the strong reduction of powders dispersion. Voc < 250 g/l according 2004/42CE

B) TECHNICAL DATA:

| | |
|-------------------|---------------------------------------------------|
| Composition | Unsaturated polyestere resins and special fillers |
| Specific weight | 1.0 ± 0,05 |
| Available colours | Yellow |
| Safety data | See safety data sheet |

C) SURFACE PREPARATION :



- * Galvanized sheets, aluminium and its alloys, iron, steel plates, plastics
- * Original paints or aged topcoat finishes



- * Clean well the surface to be treated with V09 Antisil. Make sure it is dry and free from silicone, wax, grease and any extraneous material.

- * On base coats or enamel top coats, sand and clean the surface before applying the filler.

D) CAUTIONS:

- * Mix well the filler with 1-3% paste hardener. Do not exceed with the hardener to avoid risk of staining during the painting operations.
- * Do not use the product at temperatures below 5°C.
- * Store in a cool and dry place.



E) PROCESSING:



1-3% paste hardener - potlife 3-5' a 20° C.



application with putty knife



< 30' at 20° C.



4-5' at 1 mt.



P60-P120 coarse sanding
P180-P220 finishing

F) TOOLS CLEANING:

* With nitro or washing thinner.

G) RECOATING :

A14, A15 Primer
F18 Spray putty
F09, F30, F31, F32, F35, F36 Polyuretane primers
F04, F16, F02, F57, F58, F59, F90 Acrylic primers
F06 colourable acrylic primer

Technical indications and advices are based on our own experiences. We assure the perfect quality of products. However, being the utilization out of our control, we assume no responsibility on the results obtained